

Michigan Technological University
Digital Commons @ Michigan Tech

Department of Physics Publications

Department of Physics

10-21-2013

Formation of nanodiamonds at near-ambient conditions via microplasma dissociation of ethanol vapour

Ajay Kumar Case Western Reserve University

Pin Ann Lin Case Western Reserve University

Albert Xue Case Western Reserve University

Boyi Hao Michigan Technological University

Yoke Khin Yap Michigan Technological University

See next page for additional authors

Follow this and additional works at: https://digitalcommons.mtu.edu/physics-fp

Part of the Physics Commons

Recommended Citation

Kumar, A., Lin, P. A., Xue, A., Hao, B., Yap, Y. K., & Sankaran, R. M. (2013). Formation of nanodiamonds at near-ambient conditions via microplasma dissociation of ethanol vapour. *Nature Communications, 5*, 2618. http://dx.doi.org/10.1038/ncomms3618

Retrieved from: https://digitalcommons.mtu.edu/physics-fp/294

Follow this and additional works at: https://digitalcommons.mtu.edu/physics-fp Part of the <u>Physics Commons</u>

Authors

Ajay Kumar, Pin Ann Lin, Albert Xue, Boyi Hao, Yoke Khin Yap, and R. Mohan Sankaran



ARTICLE

Received 26 Feb 2013 | Accepted 16 Sep 2013 | Published 21 Oct 2013

DOI: 10.1038/ncomms3618

Formation of nanodiamonds at near-ambient conditions via microplasma dissociation of ethanol vapour

Ajay Kumar¹, Pin Ann Lin¹, Albert Xue¹, Boyi Hao², Yoke Khin Yap² & R. Mohan Sankaran¹

Clusters of diamond-phase carbon, known as nanodiamonds, exhibit novel mechanical, optical and biological properties that have elicited interest for a wide range of technological applications. Although diamond is predicted to be more stable than graphite at the nanoscale, extreme environments are typically used to produce nanodiamonds. Here we show that nanodiamonds can be stably formed in the gas phase at atmospheric pressure and neutral gas temperatures <100 °C by dissociation of ethanol vapour in a novel microplasma process. Addition of hydrogen gas to the process allows in flight purification by selective etching of the non-diamond carbon and stabilization of the nanodiamonds. The nanodiamond particles are predominantly between 2 and 5 nm in diameter, and exhibit cubic diamond, *n*-diamond and lonsdaleite crystal structures, similar to nanodiamonds in the cosmos, and offer a simple and inexpensive route for the production of high-purity nanodiamonds.

¹ Department of Chemical Engineering, Case Western Reserve University, 10900 Euclid Avenue, Cleveland, Ohio 44106 7217, USA. ² Department of Physics, Michigan Technological University, 1400 Townsend Drive, Houghton, Michigan 49931, USA. Correspondence and requests for materials should be addressed to R.M.S. (mohan@case.edu).

arbon exists as a variety of different forms at the bulk and nano scale including graphite, diamond, fullerenes, carbon nanotubes, graphene and nanodiamonds. Graphitic carbon is known to be the most stable form of bulk carbon at ambient temperature and pressure, with high pressures and high temperatures typically required to convert non-diamond phases to diamond^{1,2}. Atomistic models have predicted that at the nanoscale, hydrogen-terminated tetrahedral hydrocarbons, precursors to diamond phases, are thermodynamically more stable than polycylic aromatics, precursors to graphitic phases, with a transition in the phase stability occurring at $\sim 3 \text{ nm}$ (ref. 3). This idea supports the existence of naturally formed diamond clusters, referred to as nanodiamonds, in petroleum⁴, interstellar dust⁵ and candle flames,⁶ all presumably formed at pressures and/or temperatures outside the stability field of bulk diamond.

Nanodiamonds have been synthesized for research by several methods including detonation of carbon-containing explosives^{7,8} and plasma-enhanced chemical vapour deposition (PECVD)⁹. Despite the predicted stability of nanodiamonds, these processes require high pressure and/or high temperature and produce mixtures of non-diamond and diamond phases¹⁰. Detonation synthesis is carried out at extremely high pressures and temperatures and produces soot containing large quantities of graphitic carbon in addition to the diamond phase⁷. PECVD produces films of amorphous carbon (a-C) with nanodiamonds embedded at the grain boundaries by deposition at high temperatures⁹. Alternatively, it is known that nanoparticles can be homogeneously nucleated in a plasma process¹¹, which has the potential to produce nanodiamonds at significantly lower pressures and temperatures and higher purities. However, this

approach has thus far been limited to non-diamond carbon^{12} and larger diamond particles $(\sim\!0.1\,\mu m)^{13,14}$.

Here we report the synthesis of nanodiamonds at near-ambient conditions using a novel continuous atmospheric pressure, microscale plasma (microplasma) process. Particles are homogeneously nucleated by dissociating ethanol vapour and rapidly quenched with reaction times <1 ms to limit the size of the particles to the nanometre-size regime. By adding H₂ gas, the non-diamond phase is etched and the diamond phase is stabilized, leading to a highly purified as-grown nanodiamond product. The particles exhibit a uniform diameter of ca. 3.0 nm consistent with theoretical predictions^{3,15}, and cubic diamond, lonsdaleite and the less frequently observed *n*-diamond phases similar to presolar nanodiamonds recovered from meteorites¹⁶. The formation of nanodiamonds at near-ambient conditions confirms their remarkable stability and could help realize new technologies such as drug delivery and the coating of polymeric substrates.

Results

Gas-phase nucleation and *in situ* aerosol measurements. The experimental set-up for the synthesis of nanodiamonds is schematically illustrated in Fig. 1a. This method has been previously applied to the synthesis of silicon nanoparticles with diameters <5 nm (ref. 17). To nucleate and grow carbon nanoparticles, mixtures of Ar and H₂ gas and ethanol vapour were continuously introduced and dissociated in the microplasma at atmospheric pressure and near-ambient neutral gas temperature (Supplementary Fig. S1). Ethanol was chosen as the carbon precursor for several reasons. First, ethanol has been detected in



Figure 1 | Gas-phase nucleation and *in situ* characterization of carbon nanoparticles. Carbon nanoparticles are synthesized in the gas phase by continuously dissociating a mixture of Ar, H₂ gas and ethanol vapour in an atmospheric pressure microplasma (**a**). Scale bar, 5 mm. The aerosol particles are collected as a dry product by filtration. Aerosol size classification confirms nanoparticle formation and shows that the addition of H₂ gas reduces the particle concentration and geometric mean diameter (D_{pg}). Error bars correspond to the standard error calculated from the geometric standard deviation (σ_g). Scale bar, 5 mm. (**b**). Dissociation of ethanol vapour is monitored by OES (**c**). The C₂ band, which has been linked to nanodiamond formation, is clearly observed from 460 to 570 nm (left panel). The addition of H₂ gas results in the appearance of the H_a Balmer line at 656 nm, confirming atomic hydrogen (right panel).

interstellar gas and thus simulates a potential chemical environment for nanodiamond formation in outer space¹⁸. Second, the C:H:O ratio of ethanol is within the predicted composition range for solid carbon precipitation¹⁹ and, by adding H_2 , the ratio can be systematically tuned from non-diamond to diamond phase growth. Finally, ethanol has a suitable vapour pressure, not too high, resulting in excessive soot formation, but not too low, preventing particle nucleation. When ethanol vapour was introduced into the microplasma, the discharge turned a bright blue-green colour as a result of C₂ emission (see Fig. 1a). The neutral species gas temperature was estimated to be <100 °C using an infrared camera (FLIR, Inc.; Supplementary Fig. S2). The particles were collected at atmospheric pressure and room temperature by filtering the exiting aerosol flow with a fibre glass filter (see Fig. 1a). Particle formation was monitored in situ by aerosol size classification using a commercial scanning mobility particle sizing (SMPS) system. Figure 1b shows particle size distributions (PSDs) for nanoparticles synthesized from 180 p.p.m. ethanol vapour in Ar and 180 p.p.m. ethanol vapour mixed with 450 and 10,000 p.p.m. H₂ gas in Ar. The PSDs represent an average of 10 scans collected by SMPS characterization after steady-state operation of the microplasma was reached. The raw data were fit to log-normal distributions to obtain the geometric mean diameters (D_{pg}) and s.d. (σ_g) . We note that no particles were detected by the SMPS system for a pure Ar microplasma. The introduction of ethanol vapour produces a well-defined PSD, with a D_{pg} of 8.3 nm at steady state. The addition of H₂ reduces the overall particle concentration and the D_{pg} to 6.9 nm. Further increase in the gas-phase H₂ concentration to 10,000 p.p.m. completely quenches particle formation (see Fig. 1b). These results are consistent with the C-H-O phase diagram for carbon growth that shows increasing H with respect to C in the gas phase eventually suppresses solid carbon nucleation¹⁹.

OES of precursor dissociation. The dissociation of ethanol vapour and H₂ gas by the microplasma was confirmed by optical emission spectroscopy (OES). Figure 1c shows spectra collected from the microplasma for varying mixtures of Ar, ethanol vapour and H₂ gas. All spectra show evidence of lines corresponding to Ar $4p \rightarrow 4s$ transitions in the higher wavelength regions (665– 815 nm) (ref. 20). When ethanol is introduced, additional peaks corresponding to the C₂ swan band between 460 and 570 nm (see left panel of Fig. 1c) and CH modes at 387 and 431 nm are observed (Supplementary Fig. S3a). In addition, we detect excited H₂ from the Fulcher- α band system ~600 nm (Supplementary Fig. S3b)²⁰. The confirmation of C_2 and CH radicals is particularly important for nanodiamond formation. Previous reports have shown that C2 species initially nucleate a solid carbon cluster, and CH species form a hydrocarbon layer, promoting the nucleation of nanodiamonds^{20,21}; however, these experiments were carried out on films where the substrate may also influence nucleation^{22,23}. The addition of H_2 gas results in a new feature in the OES spectra at 656 nm corresponding to the H_{α} Balmer line (see right panel of Fig. 1c). To quantify this observation, we compared the relative intensity of the H_{α} line with an Ar-excited neutral line at 750.1 nm as a function of the gas-phase concentration of H₂ (Supplementary Fig. S4). Increasing the H₂ gas concentration is found to increase the intensity of the H_{α} line and decrease the H_2 band intensity, which indicates that dissociation to atomic hydrogen is a more favourable reaction channel than molecular excitation. The increase in atomic hydrogen coincides with a decrease in the particle diameter (see Fig. 1b). Atomic hydrogen has been previously linked in CVD diamond growth to suppression of surface reconstruction²⁴, etching of non-diamond (sp²) carbon^{20,25} and

formation of surface radical sites by hydrogen abstraction⁷, suggesting that the smaller particle size corresponds to selective removal of the non-diamond phase and stabilization of the diamond phase in our as-grown material.

Ultraviolet micro Raman spectroscopy. The structure of the asgrown carbon nanoparticles was initially analysed by micro Raman spectroscopy. Ultraviolet (UV) excitation (325 nm) was employed to enhance the scattering from the sp³ fraction in the samples²⁶. Raman spectra are shown in Fig. 2a for carbon nanoparticles synthesized with only ethanol vapour (black) and a mixture of ethanol vapour and H₂ gas (red). Both spectra exhibit two broad features, one between 1,300 and $1,400 \text{ cm}^{-1}$ and another at \sim 1,600 cm⁻¹, close to the D (disorder) and G (graphite) bands, respectively, which arise from K-point phonon scattering of A1g symmetry and zone centre phonon scattering of E_{2g} symmetry, respectively, for sp² carbon materials. The first feature also overlaps with the well-known Raman scattering peak for bulk diamond at 1,332 cm⁻¹ (ref. 26). The addition of H₂ gas is found to increase the peak intensity ratio of the first to the second feature, and shift the peak of the first feature to lower wavenumbers by ~ 40 cm⁻¹. A similar shift was also observed at other excitation wavelengths (Supplementary Fig. S5). A small shift in the peak of the second feature from 1,593 to $1,603 \text{ cm}^{-1}$ is also observed and maybe related to in-plane stretching of sp² carbon atoms resulting from strain introduced by the incorporation of hydrogen in the as-grown material. To further analyse the spectra, we deconvoluted and fit the features to Gaussian-Lorentzian curves (Supplementary Table S1). As shown in the left inset of Fig. 2a, the spectrum for nanoparticles synthesized with only ethanol vapour consists of a peak at 1,397 cm⁻¹ that can be assigned to a-C, and a weaker peak at 1,328 cm⁻¹. In comparison, the spectrum for nanoparticles synthesized with H₂ gas consists of two peaks at 1,307 and 1,372 cm⁻¹ (right inset of Fig. 2a), the former being significantly shifted to lower wavenumber and broadened. The confinement of optical phonons in nanodiamonds is known to cause a particle size-dependent shift to lower wavenumbers and broadening of the Raman scattering peak for bulk diamond²⁷. Using a recently reported model²⁸, we simulated Raman spectra as a function of nanodiamond particle size (Supplementary Fig. S6). The calculated peak position and full width half maximum (FWHM) for 2.5-nm-diameter particles, 1,311 and 90 cm⁻¹ (Supplementary Table S2 and Supplementary Fig. S7), respectively, were found to agree well with our experimentally observed peak $(1,307 \text{ cm}^{-1}, \text{FWHM} = 102 \text{ cm}^{-1})$. We also obtained UV micro Raman spectra of commercial nanodiamond samples (Supplementary Fig. S8a). A similar analysis showed that the commercial samples primarily contain particles between 4 and 6 nm, larger than the particles found in our samples (Supplementary Fig. S8b,c).

X-ray diffraction. Figure 2b shows X-ray diffraction (XRD) patterns of the same two samples of carbon nanoparticles that were characterized by Raman spectroscopy. The XRD pattern for nanoparticles synthesized with only ethanol vapour (black) shows a broad peak at ~25°, indicating that the material is mostly a-C, consistent with Raman analysis. In comparison, carbon nanoparticles synthesized from a mixture of ethanol vapour and H₂ gas (red) exhibit clear diffraction peaks corresponding to lattice planes of various phases of diamond. A higher fraction of nanodiamonds in the sample grown with H₂ gas agrees with Raman analysis. The XRD peaks at 44.1°, 51.4° and 75.8° can be assigned to the (111), (002) and (220) lattice planes of cubic diamond, with a lattice parameter of 3.55 Å. We note that the (002) plane is a forbidden reflection for cubic diamond



Figure 2 | Material characterization of carbon nanoparticles. (a) Micro Raman spectra of carbon nanoparticles synthesized with only ethanol vapour (black) and with ethanol vapour and H₂ gas (red). The addition of H₂ gas results in a shift of the broad feature near 1,400 cm⁻¹ to lower wavenumber. Deconvolution and fitting of this feature shows (inset of **a**) evidence of a peak at $1,307 \text{ cm}^{-1}$ that agrees with phonon-confined scattering from nanodiamonds²⁸. Excitation wavelength of 325 nm was used for all Raman spectra. (b) XRD patterns of carbon nanoparticles synthesized with only ethanol vapour (black) shows no crystalline peaks, suggesting an amorphous material. In comparison, the addition of H₂ gas results in crystalline peaks (red) that can be indexed to crystalline planes of lonsdaleite (L) and cubic diamond (CD) phases. (c,d) High-resolution C 1s XPS spectra of carbon nanoparticles synthesized with only ethanol vapour (c) and with ethanol vapour and H_2 gas (**d**). The different components corresponding to various chemical shifts of carbon bonds are indicated. The addition of H₂ gas increases the ratio of the sp³/sp²-hybridized carbon peak.

and corresponds to the n-diamond phase²⁹. The stability of *n*-diamond is a point of contention, but its existence has been reported in both experiments³⁰ and theoretical calculations³¹. The structure of n-diamond is believed to be face-centered cubic, with hydrogen atoms incorporated into the cubic carbon lattice³⁰. The formation of *n*-diamond is consistent with the increase in the concentration of atomic hydrogen with the addition of H₂ gas detected by OES. The peaks at 41.9° and 44.1°, the latter of which overlaps with cubic diamond, indicates the presence of lonsdaleite, with lattice constants of a = 2.49 Å and c = 4.11 Å (ref. 32). A mechanism for formation of lonsdaleite is not known, but this diamond phase is often found in meteorite samples¹⁶. In comparison, XRD patterns of commercial nanodiamond samples only showed the presence of the cubic phase (Supplementary Fig. 9). We note that all XRD peak positions are slightly shifted towards higher 2θ values as compared with bulk diamond, highlighting the nanoscale nature of our material and suggesting lattice compression due to surface stresses.

X-ray photoelectron spectroscopy. The purity of the diamondphase in the as-synthesized carbon nanoparticles was assessed by X-ray photoelectron spectroscopy (XPS)^{33,34}. From survey spectra, the metal content was found to be <0.1% in all samples (Supplementary Table S3 and Supplementary Fig. S10). Figure 2c,d shows high-resolution C 1s XPS spectra collected from carbon nanoparticles synthesized with only ethanol vapour and a mixture of ethanol vapour and H₂ gas, respectively. XPS has been previously used to characterize the carbon bonding in a-C^{33,35} and nanodiamond powders using C 1s spectra^{34,36,37}. Although XPS is generally known to probe the surface of materials, for carbon materials the inelastic mean-free path of C 1s photoelectrons is \sim 3 nm. Thus, the whole volume of small nanoparticles, as in the case of our samples, was probed³⁴. The C 1s signal of both samples consists of four chemically shifted components: peaks at ~284.0 and 285.0 eV corresponding to sp²and sp³-hybridized carbon, respectively, and peaks at 286.1 and 287.4-287.7 eV corresponding to various hydrogen and oxygen functionalities including C-H, C-OH, C-O-C and C = O, in order of increasing binding energies. These peak shifts are in agreement with previous studies of nanodiamonds^{34,37}. We focused our analysis on the sp^2 and sp^3 carbon peaks that arise from the presence of graphitic and diamond phases, respectively, in the samples. The sp³/sp² carbon ratio increases substantially from 1.6 to 5.5 with the addition of H₂ gas, corresponding to an increase in the fraction of sp³ carbon relative to sp² carbon from ~ 61 to 85% (Supplementary Table S4). We validated the reliability of XPS to assess the purity of the diamond phase with respect to the graphitic phase by also characterizing several commercially available nanodiamond samples and found excellent agreement with reported values (Supplementary Fig. S11)38. Overall, our XPS results confirm that the addition of H₂ gas improves the assynthesized purity of the nanodiamonds relative to non-diamond carbon. Although atomic hydrogen has been previously used to treat nanodiamond powder and remove sp² carbon³⁹, the key difference is that in our process the nanodiamonds are purified in flight.

Transmission electron microscopy. Additional microstructural characterization of our material was performed at the nanoscale by transmission electron microscopy (TEM). Figure 3a,b shows representative TEM images of carbon nanoparticles synthesized from only ethanol vapour and drop-cast on carbon-coated Cu grids from a solution dispersion. The nanoparticles are unagglomerated (Fig. 3a), uniformly sized (Fig. 3b) and crystalline, as



Figure 3 | TEM analysis of carbon nanoparticles. Representative TEM image of as-grown carbon nanoparticles synthesized by dissociation of only ethanol vapour in an atmospheric pressure microplasma shows evidence of unagglomerated, nanosized particles (a). The particles are roughly spherical and highly uniform in size. Scale bar, 20 nm. (b). SAED confirms that the particles are crystalline (inset of b). EDX shows that the particles are metal-free (Cu peaks are from the TEM grid). Scale bar, 5 nm (c). Histogram of the particle diameters as measured from TEM analysis of ~250 particles shows that the particles are primarily between 2 and 5 nm (d).

confirmed by selected-area electron diffraction (SAED; inset of Fig. 3b). The chemical composition of the particles was assessed by energy-dispersive spectroscopy (EDX). The EDX spectrum in Fig. 3c shows that the particles are free of impurities, in support of XPS results; peaks in the spectra from copper and oxygen are always present from the Cu grid and O2 gas in the instrument background. A histogram obtained by sizing and counting ~ 250 individual particles from TEM images shows that the nanoparticles are mostly between 2 and 5 nm diameter (>90%). The monodispersity of the particles supports the existence of a 'magic' cluster size¹⁵. Figure 4 shows high-resolution TEM analysis of individual particles whose random orientation allowed lattice fringes to be observed. The measured lattice spacings match up well with lattice planes of various diamond phases including lonsdaleite (100) (2.17 Å), cubic diamond (111) or lonsdaleite (002) (2.07 Å), lonsdaleite (101) (1.93 Å) and cubic diamond (002) (1.76 Å). The latter suggests the presence of the previously described *n*-diamond phase. We performed similar single-particle lattice spacing measurements on ~ 50 particles and combined this analysis with SAED and XRD to statistically assess the crystal structure of the nanodiamonds in our samples (Supplementary Table S5 and Supplementary Figs S12–S16). Table 1 summarizes the measured d spacings, all of which within error compare favourably with reported values for cubic diamond, n-diamond and lonsdaleite^{2,40}.

A small number of particles were appropriately oriented with the electron beam in TEM to allow more than one crystal plane of individual particles to be resolved. Figure 5a,b shows highresolution transmission electron microscopy images of two representative particles, both 3 nm in diameter. From the fast



Figure 4 | High-resolution TEM of nanodiamonds. Measured lattice spacings of single particles correspond to the lonsdaleite (100) (**a**), cubic diamond (111) or lonsdaleite (002) (**b**), lonsdaleite (101) (**c**), and cubic diamond (002) (**d**) phases. Scale bars, 2 nm.

Table 1 Crystal structure analysis.					
Measured d spacings [*] (Å)	Cubic diamond		Lonsdaleite		Frequency
	hkl	d spacing (Å)	hkl	d spacing (Å)	(%)
2.16-2.20 2.04-2.08	111	2.06	100 002	2.18 2.06	26.3 39.5
1.90-1.96 1.74-1.78	002	1.78 [†]	101	1.93	23.7 10.5
1.51			102	1.5	—
1.25-1.31 1.15-1.18	022	1.26	110 103	1.26 1.16	
1.06	113	1.075	112	1.075	_

Summary of measured d spacings of carbon nanoparticles and comparison with reported d spacings for cubic diamond and lonsdaleite. The frequency was obtained from TEM analysis of \sim 50 individual particles.

*Compilation of values from SAED, XRD and TEM analysis

[†]Forbidden cubic diamond reflection (*n*-diamond).

Fourier transform images (FFT; see insets of Fig. 5a), we determined that the particles are lonsdaleite and n-diamond, imaged along the (010) and (110) zone axes, respectively. The measured lattice spacings from the corresponding inverse FFT images shown in Fig. 5c,d validate the crystalline structure and are in excellent agreement with SAED and XRD results (see Table 1).

Carbon nanoparticles synthesized by adding H_2 gas to the ethanol vapour in the microplasma were also analysed by TEM (Supplementary Fig. S17). In comparison with carbon nanoparticles synthesized with only ethanol vapour, we observed that the samples were much cleaner (less a-C), consistent with micro Raman, XRD and XPS characterization. The particles were



Figure 5 | Single-particle analysis by FFT filtering. (**a**,**b**) High-resolution transmission electron microscopy images of two nanodiamond particles aligned with the electron beam and imaged along the (010) (**a**) and (110) (**b**) zone axes. Corresponding FFT images (insets of **a**,**b**) and inverse FFT images (**c**,**d**) confirm that the particles are lonsdaleite (**a**,**c**) and *n*-diamond (**b**,**d**), respectively. Scale bars, 2 nm.

unagglomerated and crystalline, with similar particle sizes and crystal structures as those synthesized with only ethanol vapour (Supplementary Fig. S18). Commercial nanodiamond samples imaged by TEM were found to be comparatively larger in size (>5 nm), in agreement with Raman characterization, and severely agglomerated (Supplementary Fig. S19).

Discussion

There are several possible reasons why our process is capable of producing nanodiamonds at near-ambient conditions. The microplasma process is comparable to PECVD and the combination of plasma dissociation and gas-phase chemistry may aid the nucleation of diamond-phase carbon analogous to chemical vapour deposition (CVD) diamond¹⁹. Similar to CVD, atomic hydrogen may kinetically etch the non-diamond sp² carbon and allow diamond-phase sp³ carbon to grow¹. Hydrogen may also help stabilize the surface of the nanodiamonds³. Previous attempts to synthesize carbon nanoparticles by homogeneous nucleation have produced graphene¹² or much larger diamond particles¹⁴. The formation of nanodiamonds in a microplasma underscores the importance of quenching, which maybe essential to limiting the particle size to diamond's predicted thermodynamic stability at the nanoscale³. Future studies are required to more carefully clarify the mechanism for nanodiamond formation in our process and, in particular, separate these kinetic and thermodynamic considerations.

The formation of nanodiamonds at near-ambient conditions has wide-ranging scientific implications. Our experimental confirmation of diamond-phase carbon produced at conditions far from its bulk thermodynamic stability provides support for theoretical predictions, and, importantly, the size at which this occurs $(ca. 3 \text{ nm})^3$. The 'magic' size¹⁵ and structure of the material, including the more rare lonsdaleite phase, is consistent

with characterization of interstellar diamond¹⁶ and suggests that a high-pressure history is not needed to explain their existence⁴¹. The evidence for gas-phase nucleation in a plasma environment brings into question how diamond maybe nucleated in conventional CVD processes⁹ and suggests that diamond particles could in some cases nucleate first in the gas phase, subsequently deposit on the substrate and act as seeds for film growth.

The process we have developed should also have several technological benefits. Compared with CVD, nanodiamonds are synthesized continuously at atmospheric pressure and as a powder. By fabricating arrays of microplasmas, it should be possible to produce large mass amounts $(>1 \text{ g h}^{-1})^{42}$. The nanodiamonds are produced at significantly lower temperatures, which should enable the coating of plastics for flexible applications⁴³. Compared with detonation, the microplasma process is higher purity as metal and other impurities (for example, nitrogen and oxygen) are eliminated⁴⁴. Moreover, steep pressure and temperature gradients are avoided, which in detonation processes lead to fullerene shells and severe agglomeration, requiring extensive post-purification steps⁴⁵. Through the addition of H₂ gas, we have shown a path to improve the purity of the diamond phase in flight, as opposed to acid treatment⁴⁵ and air oxidation³⁸. Finally, our results indicate that the nanodiamonds produced by the microplasma process are significantly smaller than currently available material¹⁰. Such particles may facilitate biological applications where the particle size is critical to transport and drug delivery⁴⁶. Overall, these differences suggest that it maybe possible through future studies to further tune and optimize the microplasma process to ultimately control the particle size, surface chemistry and doping (for example, nitrogen) of the nanodiamonds for a wide range of applications.

Methods

Microplasma synthesis and aerosol mobility measurements. Carbon nanoparticles were synthesized in the gas phase at atmospheric pressure and room temperature by continuously dissociating ethanol vapour in a microplasma. The microplasma was formed between a stainless steel capillary tube (outer diameter = 1.59 mm, inner diameter = 0.178 mm) and a stainless steel mesh $(2 \times 4 \text{ mm}^2)$ electrode, operated as the cathode and anode, respectively. The electrodes were separated by a gap of 2 mm and sealed inside a quartz tube (OD = 6.35 mm) with Swagelok gas fittings. The microplasma was ignited with a negatively biased, high-voltage, direct-current power supply (Power Designs Inc, Model HV-1547), ballasted by a power resistor (500 kΩ). The discharge was operated at a constant current of 3.6 mA in all experiments.

Controlled concentrations of ethanol vapour were introduced into the microplasma by bubbling Ar gas through a solution of pure ethanol (200 proof, Decon Labs, Inc.) cooled to -10 °C (*P = 0.1079 psi, 5,000 p.p.m.). This flow was then diluted twice, first with a flow of 460 s.c.c.m. Ar, and then with a flow of 55 s.c.c.m. Ar after exhausting a flow of 455 s.c.c.m. Thus, a final concentration of 180 p.p.m. ethanol in Ar at a total gas flow rate of 100 s.c.c.m. was introduced into the microplasma. From aerosol measurements, we found that this ethanol concentration was optimal to nucleate a steady-state concentration of carbon nanoparticles for over 100 h. Alternatively, we introduced H₂ gas either directly into the microplasma at a concentration of 10,000 p.p.m. or with Ar through the bubbler for a final H₂ concentration of 450–1,800 p.p.m. in the microplasma.

In situ aerosol measurements of as-synthesized carbon nanoparticles were performed with a scanning mobility particle sizer (SMPS) system (TSI, Inc., Model 3936) consisting of a differential mobility analyser and a butanol-based condensation particle counter. To avoid Brownian coagulation, the particles exiting the microplasma were diluted with a flow of N_2 gas.

Optical emission spectroscopy. OES of the microplasma was carried out by collecting the emitted light with a 600-µm-diameter fibre optic cable coupled to a spectrometer (Ocean Optics Inc., Model HR400). Line intensities were calibrated with a tungsten halogen light source. Spectra were integrated 10 times with an acquisition time of 100 ms.

Collection of carbon nanoparticles. As-synthesized carbon nanoparticles were collected by continuously trapping the aerosol product exiting the microplasma on commercial filters with pore sizes $<1 \,\mu$ m including stainless steel, polyfluorotetraethylene and glass fibre. In most cases, we used glass fibre filters (Millipore Inc.) that did not contribute any background signal in micro Raman

spectroscopy and XRD. The mass of collected product was obtained by weighing the filter before and after collection.

Micro Raman spectroscopy and phonon confinement model. Micro Raman spectroscopy was carried out at various excitation wavelengths. Excitation in the visible range was performed with an inVia Renishaw spectrometer equipped with three lasers at $\lambda = 488$, 514 and 633 nm. To enhance the scattering from the sp³ component relative to the sp² component of our material²⁶, UV excitation at $\lambda = 325$ nm was performed with a Jobin-Yvon LabRAM HR800 spectrometer.

The Raman spectra were fit to a refined phonon confinement model²⁸ for diamond, which relates the intensity of the Raman scattering to the size of the particles:

$$I(\omega) \simeq \int_{0}^{1} \frac{\exp(-q^{2}L^{2}/4)4\pi q^{2}}{[\omega - \omega(q)]^{2} + (\Gamma/2)^{2}} dq$$
(1)

where *I* is the intensity, *L* is the size of the particles, ω is the phonon dispersion curve, *q* is the wave vector and Γ is the FWHM of the scattering peak. Γ and $\omega(q)$ are given by the following polynomial functions:

$$\Gamma = A + \frac{B}{L^2} \tag{2}$$

where A = 11 cm⁻¹ and B = 491.25 cm⁻¹ and

$$\omega(q) = A + B \cdot q + C \cdot q^2 + D \cdot q^3 + E \cdot q^4 + F \cdot q^5$$
(3)

where A, B, C, D, E and F are coefficients for seven different phonon branches (Λ_1 , Λ_3 , Σ_1 , Σ_2 , Σ_3 , Δ_2 and Δ_5) corresponding to scattering from various crystalline phases of diamond.

XRD. XRD was carried out with a Scintag X-1 advanced X-ray diffractometer using monochromated Cu-K α radiation ($\lambda = 0.1542$ nm). All XRD patterns were collected from a 2 θ of 20°–80°, with a step size of 0.01°, at a grazing incident angle of 2° to enhance the sensitivity from our relatively thin samples. From the XRD peaks, *d* spacings were calculated using Bragg's equation ($n\lambda = 2d\sin\theta$). For *d* spacings corresponding to cubic or *n*-diamond, the lattice parameter, *a*, was calculated using the following equation:

$$\frac{1}{d_{hkl}^2} = \frac{\mathbf{h}^2 + \mathbf{k}^2 + \mathbf{l}^2}{a^2} \tag{4}$$

and for *d* spacings corresponding to the lonsdaleite phase of diamond, the lattice parameters, *a* and *c* were calculated using the following equation (where $a = b \neq c$):

$$\frac{1}{d_{\rm hkl}^2} = \frac{4}{3} \cdot \frac{({\rm h}^2 + {\rm hk} + {\rm l}^2)}{a^2} + \frac{{\rm l}^2}{c^2} \tag{5}$$

XPS. XPS was performed with a PHI VersaProbe using a monochromatic Al K α X-ray (1486.6 eV) source. Samples for XPS were either prepared by collecting on glass fibre filters to assess the metal impurities or directly depositing on single crystal Si substrates using a nanometre aerosol sampler (TSI, Inc., Model 3089) to characterize the relative fraction of diamond (sp³ carbon) and non-diamond (sp² carbon) phases. Before nanoparticle deposition, the Si substrates were cleaned with acetone to remove residual carbon. After deposition, the samples were sputtered inside the XPS instrument by an Ar ion beam to remove contamination (for example, adventitious carbon) that occurred during sample transfer. In all cases, spectra were taken with a spot size of 300 μ m. High-resolution C Is spectra were acquired with a step size of 0.1 eV from a minimum of two spots on each sample and averaged. The binding energies were corrected to compensate for surface charging. The spectra were deconvoluted and fit using the PHI Multipak program from ULVAC-PHI, Inc. by a Lorentz – Gauss algorithm after subtracting a Shirley background.

TEM and EDX. TEM was carried out with a Philips Tecnai F30 field-emission electron microscope operated at 300 kV. TEM samples were prepared by carefully shaking the filter-collected carbon nanoparticles in methanol and drop casting on carbon-coated Cu grids. Sonication was avoided to prevent the filter from breaking up. EDX was performed with a 130-eV energy resolution Li-drift Si detector. Additional structural information was obtained by SAED and FFT.

References

- Angus, J. C. & Hayman, C. C. Low-pressure, metastable growth of diamond and "diamondlike" phases. *Science* 241, 913–921 (1988).
- Gogotsi, Y., Welz, S., Ersoy, D. A. & McNallan, M. J. Conversion of silicon carbide to crystalline diamond-structured carbon at ambient pressure. *Nature* 411, 283–287 (2001).
- Badziag, P., Verwoerd, W. S., Ellis, W. P. & Greiner, N. R. Nanometre-sized diamonds are more stable than graphite. *Nature* 343, 244–245 (1990).

- Dahl, J. E., Liu, S. G. & Carlson, R. M. Isolation and structure of higher diamondoids, nanometer-sized diamond molecules. *Science* 299, 96–99 (2003).
- Lewis, R. S., Ming, T., Wacker, J. F., Anders, E. & Steel, E. Interstellar diamonds in meteorites. *Nature* 326, 160–162 (1987).
- Su, Z., Zhou, W. & Zhang, Y. New insight into the soot nanoparticles in a candle flame. *Chem. Comm.* 47, 4700–4702 (2011).
- Greiner, N. R., Phillips, D. S., Johnson, J. D. & Volk, F. Diamonds in detonation soot. *Nature* 333, 440–442 (1988).
- See Danilenko, V. V. On the history of the discovery of nanodiamond synthesis. *Phys. Solid State* 46, 595–599 (2004 and references therein).
- Jiao, S. *et al.* Microstructure of ultrananocrystalline diamond films grown by microwave Ar–CH4 plasma chemical vapor deposition with or without added H₂. *J. Appl. Phys.* **90**, 118–122 (2001).
- 10. Mochalin, V. N., Shenderova, O., Ho, D. & Gogotsi, Y. The properties and applications of nanodiamonds. *Nat. Nanotech.* 7, 11–23 (2012).
- 11. Kortshagen, U. Nonthermal plasma synthesis of semiconductor nanocrystals. *J. Phys. D* **42**, 113001 (2009).
- Dato, A., Radmilovic, V., Zonghoon, L., Phillips, J. & Frenklach, M. Substrate-free gas-phase synthesis of graphene sheets. *Nano Lett.* 8, 2012–2016 (2008).
- Frenklach, M. et al. Induced nucleation of diamond powder. Appl. Phys. Lett. 59, 546–548 (1991).
- 14. Vandenbulcke, L., Gries, T. & Rouzaud, J. N. Nanodiamonds in dusty lowpressure plasmas. *Appl. Phys. Lett.* **94**, 044106 (2009).
- Raty, J.-Y. & Galli, G. Ultradispersity of diamond at the nanoscale. *Nat. Mater.* 2, 792–795 (2003).
- Karczemska, A. et al. Extraterrestrial, terrestrial and laboratory diamonds Differences and similarities. Diam. Relat. Mater. 17, 1179–1185 (2008).
- Sankaran, R. M., Holunga, D., Flagan, R. C. & Giapis, K. P. Synthesis of blue luminescent Si nanoparticles using atmospheric-pressure microdischarges. *Nano Lett.* 5, 537–541 (2005).
- Ehrenfreung, P. & Charnley, S. B. Organic molecules in the interstellar medium, comets, and meteorites: a voyage from dark clouds to the early Earth. *Ann. Rev. Astron. Astrophys.* 38, 427–483 (2000).
- Bachman, P. K., Leers, D. & Lydtin, H. Towards a general concept of diamond chemical vapour deposition. *Diam. Rel. Mater.* 1, 1–12 (1991).
- Mucha, J. A., Flamm, D. L. & Ibbotson, D. E. On the role of oxygen and hydrogen in diamond-forming discharges. J. Appl. Phys. 65, 3448–3452 (1989).
- Zhou, D., Gruen, D. M., Qin, L. C., McCauley, T. G. & Krauss, A. R. Control of diamond film microstructure by Ar additions to CH₄/H₂ microwave plasmas. *J. Appl. Phys.* 84, 1981–1989 (1998).
- Wang, C. S., Chen, H. C., Shih, W.-C., Cheng, H.-F. & Lin, I. N. Effect of H₂/Ar plasma on growth behavior of ultra-nanocrystalline diamond films: The TEM study. *Diam. Rel. Mater.* 19, 138–142 (2010).
- 23. Gruen, D. M. Nanocrystalline diamond films. Annu. Rev. Mater. Sci. 29, 211–259 (1999).
- 24. Lander, J. J. & Morrison, J. Low energy electron diffraction study of the (111) diamond surface. *Surf. Sci* **4**, 241–246 (1966).
- Spitsyn, B. V., Bouilov, L. L. & Derjaguin, B. V. Vapor growth of diamond on diamond and other surfaces. J. Cryst. Growth 52, 219–226 (1981).
- Ferrari, A. C. & Robertson, J. Raman spectroscopy of amorphous, nanostructured, diamond–like carbon, and nanodiamond. *Phil. Trans. R. Soc. Lond. A* 362, 2477–2512 (2004).
- 27. Yoshikawa, M. et al. Raman scattering from nanometer-sized diamond. Appl. Phys. Lett. 67, 694–696 (1995).
- Osswald, S., Mochalin, V. N., Havel, M., Yushin, G. & Gogotsi, Y. Phonon confinement effects in the Raman spectrum of nanodiamond. *Phys. Rev. B* 80, 075419 (2009).
- 29. Hirai, H. & Kondo, K. Modified phases of diamond formed under shock compression and rapid quenching. *Science* **253**, 772–774 (1991).
- Cowley, J. M., Mani, R. C., Sunkara, M. K., O'Keeffe, M. & Bonneau, C. Structures of carbon nanocrystals. *Chem. Mater.* 16, 4905–4911 (2004).
- Singh, T., Behr, M. J., Aydil, E. S. & Maroudas, D. First-principles theoretical analysis of pure and hydrogenated crystalline carbon phases and nanostructures. *Chem. Phys. Lett.* **474**, 168–174 (2009).
- Frondel, C. & Marvin, U. B. Lonsdaleite, a hexagonal polymorph of diamond. Nature 214, 587-589 (1967).
- 33. Haerle, R., Riedo, E., Pasquarello, A. & Baldereschi, A. sp²/sp³ hybridization ratio in amorphous carbon from C 1s core-level shifts: X-ray photoelectron spectroscopy and first-principles calculation. *Phys. Rev. B* 65, 045101 (2001).
- Petit, T., Arnault, J.-C., Girard, H. A., Sennour, M. & Bergonzo, P. Early stages of surface graphitization on nanodiamond probed by X-ray photoelectron spectroscopy. *Phys. Rev. B* 84, 233407 (2011).
- Robertson, J. Diamond-like amorphous carbon. Mater. Sci. Eng. R 37, 129–281 (2002).

ARTICLE

- Cunningham, G., Panich, A. M., Shames, A. I., Petrov, I. & Shenderova, O. Ozone-modified detonation nanodiamonds. *Diam. Rel. Mater.* 17, 650–654 (2008).
- 37. Butenko, Y. V. et al. Photoemission study of onionlike carbons produced by annealing nanodiamonds. Phys. Rev. B 71, 075420 (2005).
- Osswald, S., Yushin, G., Mochalin, V., Kucheyev, S. O. & Gogotsi, Y. Control of sp²/sp³ carbon ratio and surface chemistry of nanodiamond powders by selective oxidation in air. *J. Am. Chem. Soc.* **128**, 11635–11642 (2006).
- Yeganeh, M., Coxon, P. R., Brieva, A. C., Dhanak, V. R., Siller, L. & Butenko, Y. V. Atomic hydrogen treatment of nanodiamond powder studied with photoemission spectroscopy. *Phys. Rev. B* 75, 155404–155412 (2007).
- Dai, Z. R. et al. Possible in situ formation of meteoritic nanodiamonds in the early solar system. Nature 418, 157–159 (2002).
- 41. Marks, N. A., Lattemann, M. & McKenzie, D. R. Nonequilibrium route to nanodiamond with astrophysical implications. *Phys. Rev. Lett.* **108**, 075503 (2012).
- 42. Mariotti, D. & Sankaran, R. M. Microplasmas for nanomaterials synthesis. *J. Phys. D* **43**, 323001 (2010).
- Lam, R. *et al.* Nanodiamond-embedded microfilm devices for localized chemotherapeutic elution. ACS Nano 2, 2095–2102 (2008).
- Krüger, A. The structure and reactivity of nanoscale diamond. J. Mater. Chem. 18, 1485–1492 (2008).
- Krüger, A. *et al.* Unusually tight aggregation in detonation diamond: identification and disintegration. *Carbon N. Y.* **43**, 1722–1730 (2005).
- 46. Chow, E. K. et al. Nanodiamond therapeutic delivery agents mediate enhanced chemoresistant tumor treatment. Sci. Trans. Med. 3, 73ra21 (2011).

Acknowledgements

This work is supported by the NSF CAREER Award Program under Award number CBET-0746821 and the AFOSR Young Investigator Program under Award number FA9550-10-1-0160. We acknowledge A. Avishai and R. Sharghi-Moshtaghin in the Swagelok Center for Surface Analysis of Materials (SCSAM) at Case Western for technical assistance with TEM. We are grateful to J.Angus for valuable discussions.

Author contributions

R.M.S. conceived the idea. A.X. and A.K. designed and tested the experimental system. A.K. performed aerosol measurements, OES, micro Raman, XRD, TEM and XPS, and analysed all the data. P.A.L. contributed to TEM images and analysis. B.H. and Y.K.Y. performed UV micro Raman spectroscopy. A.K. and R.M.S. wrote the paper. All authors contributed to editing of the manuscript.

Additional information

Supplementary Information accompanies this paper at http://www.nature.com/ naturecommunications

Competing financial interests: The authors declare no competing financial interest.

Reprints and permission information is available online at http://npg.nature.com/ reprintsandpermissions/

How to cite this article: Kumar, A. *et al.* Formation of nanodiamonds at near-ambient conditions via microplasma dissociation of ethanol vapour. *Nat. Commun.* 4:2618 doi: 10.1038/ncomms3618 (2013).



Corrigendum: Formation of nanodiamonds at near-ambient conditions via microplasma dissociation of ethanol vapour

Ajay Kumar, Pin Ann Lin, Albert Xue, Boyi Hao, Yoke Khin Yap & R. Mohan Sankaran

Nature Communications 4:2618 doi: 10.1038/ncomms3618 (2013); Published 21 Oct 2013; Updated 3 Jul 2014

During the final stages of manuscript preparation, the fast Fourier transform (FFT) filtered images in the insets of Fig. 5a,b were inadvertently switched and labelled with the wrong crystallographic indices. Our analysis and conclusions remain unchanged by this error. The correct version of Fig. 5 appears below.

